



FIBREFLEX PACKING & MFG. CO.

INCORPORATED

P.O. BOX 4646, PHILADELPHIA, PA 19127

PHONES 215-482-1490-91
215-482-1604
FAX 215-487-1220



LOCATION 5101 Umbria Street
Phila., PA 19128

WEB SITE www.fibreflex.com
E-MAIL sales@fibreflex.com

PRODUCT DATA DRG-46

PRODUCT CLASS: CORK/RUBBER

PROPERTY	TEST METNOD	RESULT	UNIT
Binder	ASTM D2000	Co-Polymer	
Density	ASTM D3676	37.5min	PCF
Density	ASTM D3676	600 MIN	kg/m3
Tensile Strength	ASTM F152	125 min	PSI
Compression 400 psi	ASTM F36	Recovery 30-50 80	Percent
Shore A Hardness	ASTM D2240	60 + - 10	Points
Flexibility	ASTM F147	3 max	Factor
Fluid Immersion 70 hrs 212 deg. F	ASTM F146	Volume	
Oil 1		-5 to + 15	Percent
Oil 3		0 to + 35	Percent
Fuel A (Room temperature for 22 hours)		-5 to + 15	Percent
Compression Set B 25% deflection, 22 hrs. 158 deg. F	ASTM D395	60 max	Percent
Temperature Range		-40 to 250	deg F
Meets Specification	P2268A		

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes. The values shown represent current production and may vary under different conditions.