



FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

347526

TEST CERTIFICATE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Pages
NTH(SR)/EL(C)/2014/253A	17.09.2014	1409640112794	01	05

Issued to & address

: M/s. METROSEAL.
28 - 30 Purdeys Way,
Purdeys Way Ind. Estt.,
Rochford, Essex,
SS4 IND, United Kingdom.

Customer's Ref. No.

: Nil, Date: 01.09.2014

Description of Test Item

: Electrical Insulating matting made of Elastomer

Identification of Test Item

: Electrical Insulating matting, Class '0'

Date of Receipt of Sample

: 02.09.2014

Method used for test/Specification

: As per IEC 61111 Edition 2.0 2009-04

Tested by

V. Sivaguru
Scientific Officer (Elect.)

Checked by

K. Jeyaraj
Scientific Officer (Elect.)

Approved by

S. B. Nandakumar
Scientist SC (Elect.)



FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

347526


तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

TEST CERTIFICATE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Pages
NTH(SR)/EL(C)/2014/253A	17.09.2014	1409640112794	02	05

1. Description of the sample :

- a. Nomenclature : Electrical Insulating matting made of Elastomer, Class '0'
b. Size : 2m x 1 m, Thickness: 3 mm,
c. Quantity : 2 Number.
d. Marking : The following markings were found on the mat.

"METRPSAL INSULATION MAT AS PER IEC 61111:2009  CLASS '0' 09/2014 PROOF TEST
5kV WITHSTAND TEST 10Kv MAX USE VOLATGE 1kV

As requested the sample has been subjected to IEC 61111 Edition 2.0 2009-04 with the results noted below.

2. Visual Inspection (Cl. 5.2)

- a. Classification : Class '0'
b. Composition : Elastomer, with slip resistance both sides
c. Dimensions : Length: 2m, Breadth: 1 m, Thickness: 3 mm,
d. Workmanship and finish : Generally Satisfactory, no harmful physical irregularities found on both surfaces

3. Tests	Observed	Specified
a. Mechanical Puncture resistance (as per cl. 5.5.2 of the specification) Test carried out on both sides of the sample on two samples. Puncture resistance in N		
i. Side 1	76	70 (Min)
ii. Side 2	76	

Tested by

V. Sivaguru
Scientific Officer (Elect.)

Checked by

K. Jeyaraj
Scientific Officer (Elect.)

Approved by

S. B. Nandakumar
Scientist SC (Elect.)



FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

347526

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

TEST CERTIFICATE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Pages
NTH(SR)/EL(C)/2014/253A	17.09.2014	1409640112794	03	05

	Observed	Specified
b. Voltage Proof test (as per cl. 5.6.2.2.2 of the specification) Mask with picture frame made up of insulating material with a opening of 762x762mm in the middle and kept on a earthed metal plate. The opening was filled by a conductive material. The sample kept on this arrangement and top electrode of size 762mm X 762mm place above this. (such arrangement shown in Picture 1) An ac voltage of 5kV (rms) at 50 Hz applied and kept constant for 3 minutes.	Withstood the test satisfactorily	Shall with stand without breakdown or flashover
c. Voltage Withstand Test (as per cl. 5.6.2.3 of the specification) Electrode: 25mm (Top) x 75mm (Bottom) An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 10kV.	Withstood the test satisfactorily	Shall with stand without breakdown or flashover
d. Ageing test (as per cl. 5.7 of specification) Sample conditioned at 70°C±2°C for 168 hours. Mechanical Puncture resistance (as per cl. 5.5.2 of the specification) Test carried out on both sides of the sample on two samples. Puncture resistance in N i. Side 1 ii. Side 2	Satisfactory 66 67	(Minimum 80% of puncture resistance before ageing) 60.8 (Min) 60.8 (Min)
e. Flame retardance test (as per cl.5.8.1 of the specification) Application of flame 10s and after withdrawal, the propagation of flame was observed for 55s and it shall not reach any point of 50mm diameter.	Satisfactory 44mm	Propagation of flame shall not reached 50 mm diameter of circle

Tested by

V. Sivaguru
Scientific Officer (Elect.)

Checked by

K. Jeyaraj
Scientific Officer (Elect.)

Approved by

S. B. Nandakumar
Scientist SC (Elect.)



FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)

347526

तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

TEST CERTIFICATE

Test Certificate No.	Date of Issue	Code No.	Page	No. of Pages
NTH(SR)/EL(C)/2014/253A	17.09.2014	1409640112794	04	05

	Observed	Specified
<p>f. Low Temperature folding test (as per cl. 5.8.2 of the specification) Sample conditioned at (-)25±3°C for 4 hours. After this the test piece folded at the midpoint and placed between two polyethylene plates and subjected to a force of 100N for 30s.</p> <p>i. Visual inspection</p> <p>ii. Voltage Withstand Test (An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 10kV).</p>	<p>Satisfactory as no crack or tear break observed</p> <p>Withstood the test satisfactorily</p>	<p>Shall not show crack or tear break observed</p> <p>Shall with stand without breakdown or flashover</p>
<p>g. Acid resistance (as per cl. 5.9 of the specification) Sample shall be immersed in Sulfuric acid solution at 23°C±2°C for 8h. after this rinsed with water and dried for 2h at 70°C.</p> <p>Mechanical Puncture resistance (as per cl. 5.5.2 of the specification) Test carried out on both sides of the sample on two samples.</p> <p>Puncture resistance in N</p> <p>i. Side 1</p> <p>ii. Side 2</p> <p>iii. Voltage Withstand Test (An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 10kV).</p>	<p>Satisfactory</p> <p>62</p> <p>62</p> <p>Withstood the test satisfactorily</p>	<p>(Minimum 75% of puncture resistance before ageing)</p> <p>57 (Min)</p> <p>57 (Min)</p> <p>Shall with stand without breakdown or flashover</p>

Tested by

V. Sivaguru
Scientific Officer (Elect.)

Checked by

K. Jeyaraj
Scientific Officer (Elect.)

Approved by

S. B. Nandakumar
Scientist SC (Elect.)



FORM NO : NTH/CHN/F5

भारत सरकार Government of India
राष्ट्रीय परीक्षण शाला (द.क्षे.)
NATIONAL TEST HOUSE (SR)
तरमणी, चेन्नई - 600 113. Taramani, Chennai - 600 113.
Phone : 22432374, 22431157 Fax : 22433158 email : nthsr@tn.nic.in

347526

TEST CERTIFICATE


Test Certificate No.	Date of Issue	Code No.	Page	No. of Pages
NTH(SR)/EL(C)/2014/253A	17.09.2014	1409640112794	05	05


h. Oil resistance (as per cl. 5.10 of the specification) Sample shall be immersed in Oil 23°C±2°C at 50% RH for 3h. after this rinsed with water and dried for 24h at 70°C. Mechanical Puncture resistance (as per cl. 5.5.2 of the specification) Test carried out on both sides of the sample on two samples. Puncture resistance in N i. Side 1 ii. Side 2 iii. Voltage Withstand Test (An ac voltage at 50 Hz applied with a rate of rise of voltage 1000V/sec. until it reaches 10kV).	Observed	Specified
	Satisfactory 61 61 Withstood the test satisfactorily	(Minimum 75% of puncture resistance before ageing) 57 (Min) 57 (Min) Shall with stand without breakdown or flashover


Note: The average ambient condition during the above test was as follows:-

Temperature : 25±2°C
Relative Humidity : 60 to 70 %

###END OF TEST CERTIFICATE###

Tested by

V. Sivaguru
Scientific Officer (Elect.)

Checked by

K. Jeyaraj
Scientific Officer (Elect.)

Approved by

S. B. Nandakumar
Scientist SC (Elect.)